

Material Composition for M20-876XXXXP

Product Information	
Part Number:	M20-876XX42P
Part Description:	2.54mm pitch Pin Header
Part Weight (g):	(0.121 * XX) + 0.4

Process Data	
Peak Reflow (Deg. C)	260°C for 10 seconds
Termination Finish	100% Tin over Nickel
RoHS Compliant? (Y/N)	Yes

Note: Tin plating is subject to 1,000ppm max Lead impurity.

Homogeneous Material Location	Weight (g)	Tolerance	Substance Name	CAS #
Contact - Brass	0.0581 * XX	3%	Copper	7440-50-8
	0.0249 * XX	2%	Zinc	7440-66-6
	0	(0.000058 * XX)g max	Lead (impurity only)	7439-92-1
	0	(0.000042 * XX)g max	Iron (impurity only)	7439-89-6
	0	(0.000084 * XX)g max	Tin (impurity only)	7440-31-5
	0	(0.000025 * XX)g max	Nickel (impurity only)	7440-02-0
	0	(0.000016 * XX)g max	Aluminium (impurity only)	7429-90-5
Contact - Plating	0	(0.000025 * XX)g max	Other Impurities	
	0.00105 * XX	10%	Nickel	7440-02-0
	0.00006 * XX	5%	Gold	7440-57-5
	0.00045 * XX	10%	Tin	7440-31-5
Moulding (total weight) Containing:	0.036 * XX	5%	30% GF Nylon 6T	
	0.018 * XX	5%	Nylon 6T	63428-83-1
	0.0108 * XX	5%	30% Glass Fibre	65997-17-3
	0.0018 * XX	5%	Antimony Trioxide	1309-64-4
	0.0054 * XX	5%	Other Brominated Flame Retardants [ISO 1043-4 Code No: FR(17)]	
Pick & Place Cap (total weight) Containing:	0.4	5%	30% GF Nylon 6T	
	0.2	5%	Nylon 6T	63428-83-1
	0.12	5%	30% Glass Fibre	65997-17-3
	0.02	5%	Antimony Trioxide	1309-64-4
	0.06	5%	Other Brominated Flame Retardants [ISO 1043-4 Code No: FR(17)]	

Material Composition for M20-876XXXXP

Product Information	
Part Number:	M20-876XX46P
Part Description:	2.54mm pitch Pin Header
Part Weight (g):	(0.121 * XX) + 0.4

Process Data	
Peak Reflow (Deg. C)	260°C for 10 seconds
Termination Finish	100% Tin over Nickel
RoHS Compliant? (Y/N)	Yes

Note: Tin plating is subject to 1,000ppm max Lead impurity.

Homogeneous Material Location	Weight (g)	Tolerance	Substance Name	CAS #
Contact - Brass	0.0581 * XX	3%	Copper	7440-50-8
	0.0249 * XX	2%	Zinc	7440-66-6
	0	(0.000058 * XX)g max	Lead (impurity only)	7439-92-1
	0	(0.000042 * XX)g max	Iron (impurity only)	7439-89-6
	0	(0.000084 * XX)g max	Tin (impurity only)	7440-31-5
	0	(0.000025 * XX)g max	Nickel (impurity only)	7440-02-0
	0	(0.000016 * XX)g max	Aluminium (impurity only)	7429-90-5
	0	(0.000025 * XX)g max	Other Impurities	
Contact - Plating	0.00105 * XX	10%	Nickel	7440-02-0
	0.00117 * XX	10%	Tin	7440-31-5
Moulding (total weight)	0.036 * XX	5%	30% GF Nylon 6T	
Containing:	0.018 * XX	5%	Nylon 6T	63428-83-1
	0.0108 * XX	5%	30% Glass Fibre	65997-17-3
	0.0018 * XX	5%	Antimony Trioxide	1309-64-4
	0.0054 * XX	5%	Other Brominated Flame Retardants [ISO 1043-4 Code No: FR(17)]	
Pick & Place Cap (total weight)	0.4	5%	30% GF Nylon 6T	
Containing:	0.2	5%	Nylon 6T	63428-83-1
	0.12	5%	30% Glass Fibre	65997-17-3
	0.02	5%	Antimony Trioxide	1309-64-4
	0.06	5%	Other Brominated Flame Retardants [ISO 1043-4 Code No: FR(17)]	

Prepared by: *M. J. Perry*

Martin J Perry, BSc(Eng) MSc CEng MIET
Compliance Specialist
ComplianceTeam@harwin.co.uk

On behalf of:

HARWIN